

Temp for Spraying Foam

For the 0.5 spray foam system:

A pre-heater temp	125 Deg F
B pre-heater temp	120 Deg F
Hose heat	120 Deg F

Also you need to mix B side product constantly while being used.

Also the Chemical temperature in the drum must be at 65 Deg F before uses. All drums must be heated 24 hours before used to 65 deg F. **Note: open bung opening to vent any drum that is being heated!!!!**

For the 1.2 spray foam system:

A pre-heater temp	130 Deg F
B pre-heater temp	125 Deg F
Hose heat	125 Deg F

Also you need to mix B side product constantly while being used.

Also the Chemical temperature in the drum must be at 65 Deg F before uses. All drums must be heated 24 hours before used to 65 deg F. **Note: open bung opening to vent any drum that is being heated!!!!**

For the 2.0 spray foam system:

A pre-heater temp	125 Deg F
B pre-heater temp	120 Deg F
Hose heat	120 Deg F

Also the Chemical temperature in the drum must be at 65 Deg F before uses. All drums must be heated 24 hours before used to 65 deg F. **Note: open bung opening to vent any drum that is being heated!!!!**